

Pro Filler W

Product properties

Medium wet room filler with good filling capacity and minimal sinking. Strong and water-resistant filler with a blue tone so that 'holidays' are easy to see and avoid. Has good adhesion and is easy to sand.

Labelling



Product use

Used for spot and fullplastering on concrete, lightweight concrete, plaster, gypsum plasterboards and previously painted surfaces in rooms exposed to changing moisture conditions, e.g. bathrooms and kitchens.

When used on gypsum plasterboard joints, the product should be used together with approved gypsum tape.

Substrate

Must be clean, dry, firm and suitable for surface treatment.

Treatment

Clean with a basic cleaning agent.

Rinse with clean water.

Sand hard, smooth surfaces.

Apply the filler and smooth it out.

Once the filler is dry, sand away any unevenness and remove sanding dust.

Prime the surface before subsequent treatment with, for example, paint, wallpaper, fabric or felt.

Remember to ventilate when you are finished.

Application

Apply and smooth with a wide spatula.

Apply a sufficient amount, work in and smooth the filler.

Risk of shrinkage where the filler is not completely dry before additional treatment.

Expected result

Even surface ready for additional treatment with a wall covering and/or suitable ceiling or wall paint in the desired colour and gloss.

Useful Information

When sanding, wear eye protection and a dust mask.

Environmental information

Minimize your paint waste by pre-estimating how much filler you need.

Remove as much filler as possible from tools before cleaning.

Filler and cleaning fluid must not be poured down drains, but collected and disposed of as environmental waste.

Empty and dry packaging should be sorted as plastic, metal handles should be removed and sorted as metal.

Store excess filler correctly so that leftovers can be used and environmental impact is minimised.

Storage

Cool, frost-free, and tightly closed

Protection equipment

Protect skin and eyes from splashes with suitable clothing, gloves and glasses.

Avoid inhalation of spray mist and grinding dust.

Wear suitable protective equipment, see safety data sheet for further information.

Technical Data

Color (plaster)	Blue toned
Density (kgs/l)	0.99
Solids Weight %	58
Solids Vol. %	56
Nominal spreading rate at 2 mm layer thickness (ltr./m²)	2
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Recoatable at 20° C, 60 % RH (Hours)	20
Fully cured at 20° C, 60 % RH (Days)	28
Adhesion on concrete (MPa)	0.86
Layer thickness (nominal mm)	2
Grain size (max. Mm)	0.2
Dilution	Do not dilute
Cleaning of Tools etc.	Water
Country of Origin	Sweden

Current TDS Version

October 2025