

Product properties

Matt extra rich priming paint that provides a saturated and uniform surface. Ensures a uniform, saturated and filled bottom that is suitable for finishing with ceiling or wall paint in the desired quality.

Product use

Priming of plaster, concrete, cardboard-coated gypsum board and filled surfaces before painting with ceiling and wall paint.
Also used for priming of glass felt, glass tissue and fiber felt.



Substrate

Must be clean, dry, solid and suitable for surface treatment.

Treatment

Remove loose material and paint by cleaning and sanding.
Remove water-soluble discolouration, nicotine, soot, dirt, grime, grease and chalking materials by cleaning.
Sand surface to matt finish as required.
Cracks, unevenness and holes must be filled.
Absorbent and porous substrates must be primed with a sealer.
Remember to ventilate after painting.

Application

Apply with brush, roller or spray.
Decide your choice of tool/utensil depending on the finish.
Material temperature for spray painting, min. 12°C.
Condensation during drying/curing must not occur.
Always perform a test treatment for a check and acceptance of adhesion and result.

Expected result

Matt, covered surface.
Finish treatment with paint in desired gloss and colour.

Environmental information

Minimize your paint waste by pre-estimating how much paint you need.
Remove as much paint as possible from tools before cleaning.
Paint and cleaning fluid must not be poured down drains, but collected and disposed of as environmental waste.
Empty and dry packaging should be sorted as plastic, metal handles should be removed and sorted as metal.
Store excess paint correctly so that leftovers can be used and environmental impact is minimised.

Storage

Cool, frost-free and tightly closed

Protection equipment

Protect skin and eyes from splashes with suitable clothing, gloves and glasses.
Avoid inhalation of spray mist and grinding dust.
Wear suitable protective equipment, see safety data sheet for further information.

Technical Data

Density (kgs/l)	1.44
Solids Weight %	64
Solids Vol. %	49
Nominal spreading rate (m²/ltr.)	8
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Drying time at 20° C, 60 % RH (Hours)	1
Recoatable at 20° C, 60 % RH (Hours)	4
Fully cured at 20° C, 60 % RH (Days)	28
Dilution	Water. May be diluted 5-10 % at spraying.
Cleaning of Tools etc.	Water
Country of Origin	Denmark

Current TDS Version

September 2025